



Lintel Cut-End Protection

DuraGal $^{\rm Ultra}$ Lintels have their cut-ends protected with a zinc-rich polyurethane primer. This primer complies with AS/NZS 3750.9:2009, Paints for steel structures Part 9: Organic zinc-rich primer, type 1 — single pack primer.

For more information contact Australian Tube Mills

Phone: (07) 3909 6600 | www.austubemills.com












Lintel Cut-End Protection

Care should be taken to avoid damaging this coating prior to installation. However should the coating be damaged it may be repaired by applying a stripe coat of Jotun Galvanite zinc-rich polyurethane primer or equivalent to a minimum 100 μ m dry film thickness¹. Prior to reinstating the coating, any surface contamination including dirt², oil² or corrosion products³ should be removed by an appropriate method. Observe normal good painting practice with respect to weather and apply strictly in accordance with the paint manufacturer's recommendations⁴.



NOTES

- 1 The application should be in one to two coats to 100 μm applied by brush or roller application.
- 2 A rag wetted with acetone or methylated spirits is a suitable removal method for dirt and oil.
- 3 Suitable tools for removing corrosion products include: power wire brush, needle gun, disc sander, angle grinder or chipping hammer.
- 4 The temperature of the substrate should be at least 5°C and a minimum 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate.



VISIT THE JOTUN WEBSITE
TO DOWNLOAD THE LATEST
MATERIAL SAFETY DATA SHEET
www.jotun.com

CONTACT JOTUN AUSTRALIA PTY LTD

sales@jotun.com.au | www.jotun.com

NEWCASTLE

Unit 2, 6 Torrens Avenue, Cardiff New South Wales 2285 Phone: +61 2 4956 5722 Fax: +61 2 4956 5962

GIPPSLAND

29 Stratton Drive, Traralgon Victoria 3844 Phone: +61 3 5176 1511 Fax: +61 3 5176 1443

CAIRNS

80 Aumuller Street, Cairns Queensland 4870 Phone: +61 7 4035 2170 Fax: +61 7 4035 2171

MELBOURNE

9 Cawley Road, Brooklyn Victoria 3025 Phone: +61 3 9314 0722 Fax: +61 3 9314 0423

SYDNEY

188 Newton Road, Wetherill Park New South Wales 2164 Phone: +61 2 9609 4951 Fax: +61 2 9609 4961

ROCKHAMPTON

28 Armstrong Street, North Rockhampton Queensland 4701 Phone: +61 428 321 4701 Phone: +61 407 004 101 Fax: +61 7 4921 0351

DERRIMUT

55 Derrimut Drive, Derrimut Victoria 3030 Phone: +61 3 9394 1800 Fax number: +61 3 9394 1031

BRISBANE

2/29 Nealdon Drive, Meadowbrook Queensland 4131 Phone: +61 7 3805 1700 Fax: +61 7 3805 1141

PERTH

15 Success Way, Henderson Western Australia 6163 Phone: +61 8 9437 4999 Fax: +61 8 9437 4988

This publication has been prepared as a guide only to assist anyone that may specify or use the products described in this publication. Accordingly, while Australian Tube Mills has endeavoured to ensure that all information provided in this publication is accurate and up-to-date, the following must be noted: this publication does not take into account any individual circumstances and is therefore not a substitute for informed or professional individual advice; the specifications and technical data relating to the products described in this publication are approximate and subject to change without notice, and users should check the currency of the information before relying upon it; and unless required by law, Australian Tube Mills does not accept any responsibility for any loss, damage or consequence resulting from the contents of this publication or from any omission of information in this publication. © Copyright Australian Tube Mills Pty Ltd. DuraGal^{Utra} is a registered trade mark of Australian Tube Mills Pty Ltd. August 2013.